



## Granular Carnallite Flux

### *End-uses*

Refining and casting of aluminium and magnesium alloys

### *Form*

Granules of molten material

### *Packing*

Big -bags or other polymer water - proof packing according to customers' requirements.

### *Specification*

Content, %				
KCL, min	MgCL <sub>2</sub> , min	MgO, max	NaCL*	Residue insoluble into water (other than MgO)
35	44	1.9	7-13	1.5
Granule size from 0.5 mm to 4 mm, min, weight %				95

\*Notice: NaCL content is provided for reference purposes only and if actual number is different, it is not considered as the defect and/or reason for claim/rejection of material