



Mg-Nd master alloy

End-use

Alloying of non-ferrous metals.

Конфигурация и вес

Trapezoidal ingots 8+/-1 kg or 12 +/- 1 kg by weight. Under proposal of the Buyer, weight of ingot could be changed.

Packing

Ingots covered with wax-paper are placed into 100, 150 or 230 litres. Under proposal of the Buyer, ingots covered with wax-paper could be strapped on pallets and covered with plastic film.

Specification

Grade	Main, %		Impurities, % max					
	Mg	Nd	Fe, max	AL, max	Ni, max	Si, max	Cu, max	∑ REM*
Mg-Nd	Remainder	20-35	0.15	0.05	0.01	0.05	0.10	2
Note:* - ∑ Ce + La + Pr								