



# Mg-Y master alloy

## End-use

Alloying of non-ferrous metals with magnesium and yttrium.

## Конфигурация и вес

Trapezoidal ingots 8+/-1 kg or 12 +/- 1 kg by weight.

## Packing

Ingots covered with wax-paper are placed into 50, 100, 150 or 230 litres drums. Under proposal of the Buyer, ingots covered with wax-paper could be strapped on pallets and covered with plastic film.

## Specification

Grade	Main, %		Impurities, % max					
	Mg	Y	Fe, max	AL, max	Ni, max	Si, max	Cu, max	Ca
Mg-Y	Remainder	20-25	0.02	0.07	0.003	0.01	0.01	0.02

Solikamsk Magnesium Works OAO  
9 Pravda Str.,618541, Solikamsk, Perm Region, RUSSIA 9  
Tel:+7 (34253) 52448/70237 Fax:+7 (34253) 52375  
E-mail: [sales@smw.ru](mailto:sales@smw.ru)  
[www.smw.ru](http://www.smw.ru)